



TECHNICAL CHARACTERISTICS MAMÜL ÜRÜN SPEĞİ

SIN SOLE (K)

TEST TYPES / TEST TİPİ	ASPECT/KRİTER	NORM	UNIT/BİRİM	STANDART
WEIGHT / AĞIRLIK		500±5%	g/m ²	ISO 2286-2
THICKNESS / KALINLIK		1,15±5%	mm	ISO 2286-3
TENSILE STRENGTH / KOPMA	ACROSS / EN	min. 240	N	ISO 1421
	ALONG / BOY	min. 280	N	ISO 1421
TEAR STRENGTH / YIRTILMA	ACROSS / EN	min. 25	N	ISO 4674-1
	ALONG / BOY	min. 25	N	ISO 4674-1
ELONGATION AT BREAK / UZAMA	ACROSS / EN	200±5%	%	ISO 1421
	ALONG / BOY	50±5%	%	ISO 1421
FLEXING ENDURANCE / BÜKÜLME DAYANIKLILIĞI	at 23°C 23°C sıcaklıkta	min. 100000	flx	ISO 5402
ABRASION RESISTANCE / AŞINMA MARTİNDALE		min. 22000	rub	ISO 5470-2
COLOR FASTNESS TO RUBBING / SÜRTÜNME RENK HASLIĞI	DRY / KURU	min. 4	gs	ISO 105-X12
	WET / ISLAK	min. 4	gs	ISO 105-X12
LIGHT FASTNESS / IŞIK HASLIĞI	LIGHT COLORS / AÇIK RENKLER	min. 3	bw	ISO 105-B02
	DARK COLORS / KOYU RENKLER	min. 5	bw	ISO 105-B02

CHEMICAL CHARACTERISTICS - KİMYASAL ÖZELLİKLER

COMPOSITION - İÇERİK	UNIT	VALUE
POLYURETHANE - POLİÜRETAN	%	3
POLYVINYL CHLORIDE - POLİVİNİLKORÜR	%	71
POLYESTER - POLİESTER	%	26
COTTON - PAMUK	%	-

CLEANING INSTRUCTION / KULLANIM TALİMATI

AZO-DYES, HEAVY METALS, PESTICIDES, PCP/TeCP, FORMALDEHYDE, PCB ARE WITHIN ALLOWABLE LIMITS IN PRODUCTS DUE TO EKO-TEX STANDART 100.

IN CASE OF COFFEE, TEA, ETC SPILLS: Use an absorbent cloth or piece of paper. Do not rub! Allow the stain to be absorbed until it is removed from the material surface. Rub very gently with a tissue paper applying gentle circular movements to remove any remaining humidity.

IN CASE OF DUST: To remove dust, it is advisable to use a vacuum cleaner or a soft brush.

Protect from direct sunlight. Do not clean with bleach or alcohol.

AZO-BOYALARI, AĞIR METALLER, PESTİSİTLER, PCP/TeCP, FORMALDEHİT, PCB, ÖKO-TEX STANDART 100'ÜN İZİN VERDİĞİ ÖLÇÜDEDİR.

KAHVE, ÇAY, VB.SIVI DÖKÜLMELERİ HALİNDE: Emiciliği yüksek olan bir bez veya kağıt kullanılmalıdır. Hemen silinmemeli, lekenin bez veya kağıt tarafından emilmesi sağlanmalıdır. Kalan nem, yumuşak bir bez ile dairesel hareketlerle hafifçe silinmelidir.

TOZLANMASI HALİNDE: Yüzeydeki toz, vakumlu temizleme aleti veya yumuşak başlıklı fırça yardımıyla temizlenmelidir.

Direk güneş ışığından korunmalıdır. Ağartıcı veya alkol ile temizlenmesi sakıncalıdır.

Valid for all colors. (Red colors may have less color fastness to rubbing)

Bütün renkler için geçerlidir. (Kırmızı renklere sürtünme renk haslığı daha düşük olabilir)